

YNS
ELEKTRONIC

Specification Sheet

FC-200

High - Performance Plastic Optical Fiber


From ESKA

1.Scope

2. Structure

Item		FC-200			
		Specification			
		Unit	Min.	Typ.	Max.
Optical Fiber	Core Material	—	Polymetyl - Methacrylate Resin		
	Cladding Material	—	Fluorinated Polymer		
	Core Refractive Index	—	1.49		
	Numerical Aperture	—	0.5		
	Refractive Index Profile	—	Step Index		
	Core Diameter	μm	1,840	1,960	2,080
	Cladding Diameter	μm	1,880	2,000	2,120
Approximate Weight		g / m	4		

Sectional View



YNS ELECTRONIC

Icerenkoy Mah. Eski Uskudar Yolu Cad No:6-7

Kadikoy - Istanbul TURKEY

Tel: +90 216 575 0590

www.yns.com.tr

3.Performance

Table2		FC-200				
		Item	Acceptance Criterion and / or [Test Condition]	Specification		
Unit	Min.			Typ.	Max.	
Maximum Rating	Storage and Operation Temperature	No Deterioration in Optical Properties*	°C	- 55	—	+ 70
	Operation Temperature under high humidity	No Deterioration in Optical Properties** [95 %RH]	°C	-	—	+ 60
Optical Properties	Transmission Loss	650 nm Collimated Light] [Standard condition] [10 m - 1 m cutback]	dB/km	—	—	200
Mechanical Characteristics	Minimum Bend Radius	Loss Increment =< 0.5 dB [Quarter bend]	mm	40	—	—
	Tensile Strength	[Tensile Force at Yield Point] [JIS C 6861]	N	224	—	—

All tests are carried out under temperature of 25°C unless otherwise specified.

* Attenuation change shall be within 10 % after 1,000 hours.

** Attenuation change shall be within 10 % after 1,000 hours, except that due to absorbed water .

YNS ELECTRONIC

Icerenkoy Mah. Eski Uskudar Yolu Cad No:6-7

Kadikoy - Istanbul TURKEY

Tel: +90 216 575 0590

www.yns.com.tr